

COMPOSIZIONE CHIMICA DA ALLUMINIO PRIMARIO/ CHEMICAL COMPOSITION PRIMARY ALUMINIUM %

Lega/Alloy	Si	Fe	Cu	Mn	Mg	Ni	Sn	Zn	Ti	Singolo/Each	Totale/ Total
AlCu50	0.1	0.25	48.0-52.0	0.1	0.1	0.1	0.1	0.1	0.1	0.04	0.10
AlMg20	0.2	0.3	0.1	0.1	18.0-22.0	0.05	0.05	0.1	0.1	0.04	0.10
AlMg25	0.15	0.25	0.05	0.05	23.0-26.0	0.05	0.05	0.05	0.05	0.04	0.10
AlSi25	23.0-26.0	0.3	0.1	0.1	0.1	0.05	0.05	0.1	0.1	0.04	0.10

COMPOSIZIONE CHIMICA DA ALLUMINIO SECONDARIO/ CHEMICAL COMPOSITION SECONDARY ALUMINIUM%

Lega/Alloy	Si	Fe	Cu	Mn	Mg	Ni	Sn	Zn	Ti	Singolo/Each	Totale/ Total
AlCu50	0.4	0.5	48.0-52.0	0.3	0.4	0.1	0.1	0.2	0.1	0.05	0.15
AlMg20	0.55	0.55	0.25	0.35	18.0-22.0	0.05	0.05	0.35	0.15	0.05	0.15
AlMg25	0.55	0.55	0.25	0.35	23.0-26.0	0.05	0.05	0.35	0.15	0.05	0.15
AlSi25	23.0-26.0	0.7	0.2	0.5	0.5	0.1	0.1	0.2	0.1	0.05	0.15

AMA Recycling sh.p.k.

1033, MARIKAJ, VORE, ALBANIA

MOBILE: +355 68 202 0946

EMAIL: info@amarecycling.al

WEB: www.amarecycling.al

CERTIFIED

Company with Management

System Certified

• ISO 14001

• ISO 9001